

SR FireGreen 37 / SD 820x Bio-based Fire-Retardant Epoxy systems



SR FireGreen 37 is fire retardant intumescent and halogen free epoxy system for hand-laminating. **SR FireGreen 37** resin offers a low smoke opacity and toxicity that will allow you to pass Aerospace fire specification **FAR 25-852** and also **UL 94 V0**. SD 820x are hand-laminating hardeners. Other possibilities for hot / fast curing cycle are possible. FireGreen resin are produce with about 25% of carbon from plant origin and have a lower environmental impact than standard Epoxy Systems. The bio-based Carbon content of our resins is certified by an independent laboratory using C14 measurements (ASTM D6866).

		SD 8205	SD 8202
Reactivity level			
Initial viscosity (mPa.s)	@ 20 °C	2300	2100
	@ 30 °C	1300	730
Pot Life	@ 20 °C	-	-
	@ 30 °C	-	-
Mixing ratio	By weight	100 / 20	100 / 20
	By volume	100 / 28	100 / 29
Maximum strength	N/mm ²	29	27
% Elongation at max strength	%	0,7	0,7
TG1 max onset	°C	90	91
Gel Time	@ 20 °C	07 h 00	10 h 00
	@ 30 °C	03 h 30	05 h 45
Time to reach 400 mPa.s	@ 20 °C	03 h 10	04 h 50
	@ 30 °C	02 h 00	03 h 20
Demold time	@ 20 °C	21 h 00	30 h 00
	@ 30 °C	10 h 30	17 h 15

FireGreen 37

- Maximum fire properties
- 24 % bio content

Hardeners :

SD 8205 – Standard


- For small and medium part, hand laminating / press / vacuum.
- Release best properties at room temp curing for 24h
- Faster hardener option available with SD 8207 B

SD 8202- very slow and low viscosity

- For medium and large parts, hand laminating / vacuum.
- Post-curing 12h at 40 °C
- Slower hardener / higher Tg options available with SD 8201 / SD 1305

Important guidelines :

- No filtering of the resin before laminating for an optimized fire performance.
- Use a stirrer with high shear to homogenize the resin before mixing with hardener.



Epoxy resin SR FireGreen 37

Appearance		thick liquid
Color		white
Viscosity (mPa.s)	@ 15 °C	14000 ± 2800
	@ 20 °C	8900 ± 1800
	@ 25 °C	6000 ± 1200
Density	@ 20 °C	1,2700
Storage (months)	@ Ta	24


Hardener(s)

		SD 8205	SD 8202
Appearance		liquid	liquid
Color		light yellow	light yellow
Gardner color		4	≤ 4
Reactivity level			
Viscosity (mPa.s)	@ 15 °C	225 ± 45	47 ± 9
	@ 20 °C	155 ± 35	34 ± 6
	@ 25 °C	110 ± 20	25 ± 5
	@ 30 °C	75 ± 15	20 ± 4
	@ 40 °C	40 ± 10	
Density	@ 20 °C	1,0390	0,9610
Refractive index	@ 25 °C	1,5145 ± 0,002	1,4838 ± ,002
Storage (months)	@ Ta	24	24


Mixe(s) SR Firegreen 37 / SD 820x

	SD 8205	SD 8202
Appearance	liquid	liquid
Color	white	white
Mixing ratio		
By weight	100 / 20	100 / 20
By volume	100 / 28	100 / 29
Initial viscosity (mPa.s) @ 20 °C	2300	2100
PP 50 mm / 10 s ⁻¹ @ 30 °C	1300	730
Density @ 20 °C	1,27	1,27


@ 20 °C



@ 30 °C



zoom @ 20 & 30 °C



Mechanical properties on cast resin :

		SR FireGreen 37 / SD 8205			SR FireGreen 37 / SD 8202		
Curing cycles		AT + 24h @ 40 °C	AT + 16h @ 60 °C		AT + 24h @ 40 °C	AT + 16h @ 60 °C	
Tensile							
Modulus	N/mm ²	4 100	4 100		4 000	4 000	
Maximum strength	N/mm ²	28	29		25	27	
Breaking Strength	N/mm ²	28	29		25	27	
Elongation at max strength	%	0,7	0,7		0,6	0,7	
Elongation at break	%	0,7	0,7		0,6	0,7	
Flexion							
Modulus	N/mm ²	3 800	3 600		3 800	3 700	
Maximum strength	N/mm ²	53	53		50	54	
Breaking Strength	N/mm ²	53	53		50	54	
Elongation at max strength	%	1,5	1,6		1,4	0,7	
Elongation at break	%	1,5	1,6		1,4	0,7	
Shear							
Breaking Strength	N/mm ²	32	34		31	34	
Compression							
Modulus	N/mm ²						
Yield strength	N/mm ²	73	77		74	78	
Offset compression yield	%	9,1	11		9,3	10,9	
Charpy impact strength							
Resilience	kJ/m ²		6		4		
DSC glass transition							
TG1 onset	°C	70	89		68	84	
TG1 max onset	°C		90			91	
DTMA glass transition							
TG tan delta	°C						
TeiG onset G'	°C						
TmG midpoint G'	°C						
TefG endpoint	°C						
TG peak G''	°C						

Tests carried out on samples of pure cast resin, without prior degassing, between steel plates.

Measures undertaken according to the following norms:

Mechanical tests:

Tension:	NF EN ISO 527-2:2012
Flexion:	NF EN ISO 178:2011
Compression:	NF EN ISO 604:2004 or NF EN ISO 844:2014 (foam product)
Charpy impact strength:	NF EN ISO 179-1:2010
Shear Strength:	ASTM D732-17 (Punch Tool)
Interlaminar shrinkage strength:	ASTM D5528-13
Toughness (GIC et KIC) :	ISO 13586:2000

Water absorption: Internal. Polymerization according to cycle, machining, weighing, time spent in distilled water at 70 °C / 48 hours, weighing 1 hour after emerging,

Bonding Strength Double lap shear:	ASTM D3528-96
	ADH = adhesive failure
	COH = cohesive failure
	TLC = thin-layer cohesive failure
	FT = fiber-tear failure.
	LFT = light-fiber-tear failure

Thermal tests:

Glass transition DSC:	NF EN ISO 11357-2:2014 -5°C to 180 °C under nitrogen gas
	T_{G1} or Onset: 1 st scan at 20 °C/min
	T_{G1} maximum or Onset: 2nd scan at 20 °C/min

Glass transition DTMA:	Temperature ramp 0 °C to 180 °C @ 2°C/min under normal atmosphere
	NF EN ISO 11357-1:2016 T_g onset G'
	ASTM D4065-12 T_g peak G''

Physical tests:

Gardner color:	NF EN ISO 4630:2016	Visual method
Refractive index:	NF ISO 280:1999	
Viscosity:	NF EN ISO 3219:1994	Rheometer 50 mm, shear 10 s ⁻¹
Density on liquids:	ISO 2811-1:2016	Pycnometer
Density on solid:	NF EN ISO 1183-3:1999	Helium Pycnometer
Density on foam:	NF EN ISO 845:2009	
Gel time:	Cross G' G''	Rheometer CP50 - Shear rate 10 s ⁻¹
Green Carbone content:	ASTM D6866-16 or XP CEN/TS 16640 Avril 2014	

TA:	Ambient temperature (20 to 25 °C)
NC:	No information Communicated
NB:	No Breaking (maximum flexion deformation : 15 %)

Table 1st page:

Pot Life:	Time to reach 50 °C or time limit for use
Gel time:	Intersection of tangents on the viscosity curve of 1 mm thick layer
Release time:	Time required to obtain sufficient mechanical strength to release
Minimum Vacuum Time:	Time in which vacuum can be applied (25000 mPa.s)
Maximum Vacuum time:	Limit time below which a vacuum can be applied (G'G'' crossing)
Optimum Infusion time:	Time to reach 400 mPa.s
Max Infusion Time:	Time to reach 25000 mPa.s
Vacuum cut-off time:	Time to reach G'G'' crossover + 20%

LEGAL NOTES:

Information given in writing or verbally, in the context of our technical assistance and our trials, does not engage our responsibility. Information is given in good faith based on SICOMIN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with SICOMIN's recommendations. We advise users of SICOMIN products to check by some practical trials that they are suitable for the intended processes and applications. The customer's storage, the use, the implementation and the transformation of the supplied products are not under SICOMIN's control and entirely under the sole responsibility of the user.

SICOMIN reserves the right to change the properties of its products. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data and tolerance may vary due to circumstances beyond our control.

If our responsibility should nevertheless be involved, it would be, for all the damages, limited to the value of the goods supplied by us and processed by the customer. We guaranty the non-reproachable quality of our products, in the general context of sales and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.